

#### Product description

Glass fibre reinforced injection moulding grade for machinery components and housings of high stiffness and dimensional stability such as lamp socket housings, cooling fans, insulating profile for aluminium window frames, water containers for automotive cooling systems, as well as electrically insulating parts.

#### Physical form and storage

The product is supplied in the form of granules with a bulk density of approx. 0.7 g/cm<sup>3</sup>. Standard packs are bag and bulk container (octagonal IBC=intermediate bulk container made from corrugated board with a liner bag). Other packaging materials and shipping in road or rail silo wagons are possible by agreement. The containers should only be opened immediately before processing or drying. To ensure that the delivered product absorbs as little moisture as possible, the containers should be stored in dry rooms and always carefully closed again after partial quantities have been withdrawn. In principle, the product can be stored for a long period of time. Containers stored in cold rooms should be equalized to ambient temperature before opening in order to avoid condensation on the granules. Regardless of the storage conditions, the product should be pre-dried according to our recommendations and the machine should preferably be loaded using a closed conveyor system.

#### Product safety

In case processing is done under conditions as recommended (cf. processing data sheet) melts are thermally stable and do not generate hazards by molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers the product decomposes on exposure to excessive thermal load, e.g. when it is overheated or as a result of cleaning by burning off. Further information is available from the safety data sheet.

#### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

## Product Information

Typical values for uncoloured product at 23 °C <sup>1)</sup>	Test method	Unit	Values <sup>2)</sup>
<b>Properties</b>			
Polymer abbreviation	-	-	<b>PA66-GF30</b>
Density	ISO 1183	kg/m <sup>3</sup>	<b>1360</b>
Viscosity number (0.5% in 96 % H <sub>2</sub> SO <sub>4</sub> )	ISO 307, 1157, 1628	cm <sup>3</sup> /g	<b>145</b>
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	<b>1.5 - 1.9</b>
Water absorption, saturation in water at 23°C	similar to ISO 62	%	<b>5.2 - 5.8</b>
Halogen content (Cl, Br, I), Schoeniger IC		mg/kg	<b>&lt; 100</b>
<b>Processing</b>			
Melting temperature, DSC	ISO 11357-1/-3	°C	<b>260</b>
MVR 275 °C/5 kg	ISO 1133	cm <sup>3</sup> /10min	<b>30</b>
Melt temperature, injection moulding/extrusion	-	°C	<b>280 - 300</b>
Mould temperature, injection moulding	-	°C	<b>80 - 90</b>
Moulding shrinkage, constrained <sup>3)</sup>	-	%	<b>0.55</b>
Moulding shrinkage (parallel)	ISO 294-4	%	<b>0.53</b>
Moulding shrinkage (normal)	ISO 294-4	%	<b>1.02</b>
injection molding, Melt temperature, recommended	-	°C	<b>290</b>
injection molding, Mold temperature, recommended	-	°C	<b>80</b>
<b>Flammability</b>			
UL 94 rating at 1,6 mm thickness	IEC 60695-11-10	class	<b>HB</b>
Automotive materials (Thickness >= 1mm) <sup>4)</sup>	ISO 3795, FMVSS 302	-	<b>+</b>
Oxygen index	ISO 4589-1/-2	%	<b>24</b>
UL 94 rating at 3.05 mm thickness	UL-94, IEC 60695	class	<b>HB</b>
UL 94 (2)	UL-94, IEC 60695	-	<b>UL</b>
<b>Mechanical properties</b>			
			<b>dry / cond.</b>
Tensile modulus	ISO 527-1/-2	MPa	<b>10000 / 7200</b>
Stress at break	ISO 527-1/-2	MPa	<b>190 / 130</b>
Strain at break	ISO 527-1/-2	%	<b>3 / 5</b>
Tensile creep modulus, 1000 h, strain <= 0.5%, 23°C	ISO 899-1	MPa	<b>* / 5300</b>
Flexural modulus	ISO 178	MPa	<b>8600 / 6500</b>
Flexural strength	ISO 178	MPa	<b>280 / 210</b>
Charpy unnotched impact strength (23°C)	ISO 179/1eU	kJ/m <sup>2</sup>	<b>85 / 100</b>
Charpy unnotched impact strength (-30°C)	ISO 179/1eU	kJ/m <sup>2</sup>	<b>70 / 70</b>
Charpy notched impact strength (23°C)	ISO 179/1eA	kJ/m <sup>2</sup>	<b>11 / 20</b>
Charpy notched impact strength (-30°C)	ISO 179/1eA	kJ/m <sup>2</sup>	<b>10 / 9.5</b>
Izod notched impact strength (23°C)	ISO 180/A	kJ/m <sup>2</sup>	<b>12 / 15</b>
Izod notched impact strength (-30°C)	ISO 180/A	kJ/m <sup>2</sup>	<b>10.4 / 10</b>
<b>Thermal properties</b>			
HDT A (1.80 MPa)	ISO 75-1/-2	°C	<b>250</b>
HDT B (0.45 MPa)	ISO 75-1/-2	°C	<b>260</b>
Max. service temperature (short cycle operation) <sup>5)</sup>	-	°C	<b>240</b>
Temperature index at 50% loss of tensile strength after 5000 h	IEC 60216	°C	<b>165</b>
Temperature index at 50% loss of tensile strength after 20000 h	IEC 60216	°C	<b>135</b>
Coefficient of linear thermal expansion, longitudinal (23-55)°C	ISO 11359-1/-2	E-6/K	<b>28</b>
Coefficient of linear thermal expansion, transverse (23-55)°C	ISO 11359-1/-2	E-6/K	<b>88</b>
Thermal conductivity	DIN 52612-1	W/(m K)	<b>0.35</b>
Specific heat capacity	-	J/(kg°K)	<b>1260</b>

### Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "\*" signifies inapplicable properties.

3) Test box with central gating, dimensions of base (107\*47\*1,5) mm, processing conditions: TM = 290°C, TW = 80°C

4) + = passed

5) Empirical values determined on articles repeatedly subjected to the temperature concerned for several hours at a time over a period of several years. Provisio Proper design and processing according to our recommendations.

BASF SE

67056 Ludwigshafen, Germany

## Product Information

Typical values for uncoloured product at 23 °C <sup>1)</sup>	Test method	Unit	Values <sup>2)</sup>
<b>Electrical properties</b>			<b>dry / cond.</b>
Relative permittivity (1 MHz)	IEC 62631-2-1	-	<b>3.7 / 4.3</b>
Dissipation factor (1 MHz)	IEC 62631-2-1	E-4	<b>210 / 810</b>
Volume resistivity	IEC 62631-3-1	Ohm*m	<b>1E13 / 1E10</b>
Surface resistivity	IEC 62631-3-2	Ohm	<b>1E12 / 1E10</b>
Comparative tracking index, CTI, test liquid A	IEC 60112	-	<b>- / 550</b>
Electric strength K20/P50, d = 0.6 - 0.8 mm	IEC 60243-1	kV/mm	<b>90 / 80</b>
Electric strength K20/K20, ( 60*60*1 mm <sup>3</sup> )	IEC 60243-1	kV/mm	<b>40 / 37</b>
Relative permittivity (100Hz)	IEC 62631-2-1	-	<b>4.2 / 9.7</b>
Dissipation factor (100 Hz)	IEC 62631-2-1	E-4	<b>120 / 1530</b>

### Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "\*" signifies inapplicable properties.

BASF SE

67056 Ludwigshafen, Germany