

Product description

Polyamide 66, reinforced with 38% of glass fiber & mineral filler, for injection molding.
ULT. 2412GM05-D BLACK is used in all sectors of industry, offering good mechanical strength, low warpage, good surface aspect & heat resistance.
This grade is widely used for
- Automotive parts: Fan & shroud, Engine cover, Timing belt cover
This product is available in black color and in colors on request.

Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

Injection Advice:

- For reinforced polyamides, BASF SE recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
- The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

Disclaimer

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and BASF SE is at their disposal to supply any additional information.

Safety Information

Detailed information regarding safety are available on the safety data sheet (MSDS). MSDS is sent with the first material order or available by contacting our customer services

Regulations Compliance

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with RoHS Directive 2011/65/EU, 2015/863 and local regulations as amended.

Customer Services

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

Product Information

Typical values for uncoloured product at 23 °C ¹⁾	Test method	Unit	Values ²⁾
General Properties			
Asia Pacific	-	-	+
Pellets	-	-	+
Physical			
Density	ISO 1183	kg/m ³	1470 / -
Mechanical properties			
			dry / cond.
Stress at break	ISO 527-1/-2	MPa	125 / -
Strain at break	ISO 527-1/-2	%	2.2 / -
Flexural modulus	ISO 178	MPa	11000 / -
Flexural modulus (ASTM)	ASTM D 790	MPa	9100 / -
Flexural strength	ISO 178	MPa	180 / -
Flexural strength (ASTM)	ASTM D 790	MPa	190 / -
Izod notched impact strength ISO 180/A (23°C)	ISO 180/A	kJ/m ²	6 / -
Izod notched impact strength ASTM D 256 (23 °C)	ASTM D 256	J/m	60 / -
Tensile strength 5mm/min (ASTM)	ASTM D 638	MPa	125 / -
Tensile elongation 5mm/min (ASTM)	ASTM D 638	%	2.5 / -
Thermal properties			
HDT A (1.80 MPa)	ISO 75-1/-2	°C	230
Melting temperature, DSC (10°C/min)	ISO 11357-1/-3	°C	262
HDT A (1.80 MPa), ASTM	ASTM D 648	°C	220
Flammability			
Burning Behav. at thickness 0.8 mm	UL-94, IEC 60695	class	HB
Burning Behav. at thickness 3.2 mm	UL-94, IEC 60695	class	HB
Injection			
Pre/Post-processing, Pre-drying, Temperature	-	°C	80 - 100
Injection molding cylinder temperature 1 (feed zone)	-	°C	270 - 275
Injection molding cylinder temperature 2 (compression)	-	°C	275 - 285
Injection molding cylinder temperature 3 (metering-zone, head room of screw)	-	°C	285 - 295
injection molding, Mold temperature, range	-	°C	80 - 100

Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "*" signifies inapplicable properties.

BASF South East Asia Pte Ltd

7 Temasek Boulevard #35-01, Suntec Tower One, Singapore 038987